

# Determination of the optimal conditions for bovine serum albumin surface enhanced Raman scattering on silver colloids and nanoparticle films

Joell D. Reyes and Brian D. Gilbert

Department of Chemistry, Linfield College, McMinnville, Oregon 97128

## Introduction

In proteomic studies, surface enhanced Raman scattering (SERS) has been used for protein identification<sup>1,2</sup>. SERS is a sensitive surface technique used to identify various molecules through the enhancement of inelastic scattering. Raman scattering occurs when adsorbed to a nanometer sized metal (typically Au or Ag) surface.

Serum albumin is essential for maintaining the osmotic pressure needed for proper distribution of body fluids between intravascular compartments and body tissues<sup>3</sup>. It also is responsible for maintaining the pH of blood and is the most abundant protein in the circulatory system<sup>4</sup>. Acidified sulfate was used as an aggregating agent for SERS of bovine serum albumin (BSA) because the sulfates have a weaker binding affinity to the metal surface<sup>5</sup>.

The purpose of this particular study is to find the optimal condition to take SERS spectra of BSA. If such conditions can be found for one particular type of protein, then one could design a systematic approach to determine label-free detection of any protein molecule.

## Materials and methods

### Silver Colloid Solution

BSA, sodium citrate, and AgNO<sub>3</sub> were used as purchased from Sigma Aldrich (Saint Louis, Missouri). Silver colloids were made with AgNO<sub>3</sub>, sodium citrate (1%), and H<sub>2</sub>O following Lee & Meisel<sup>6</sup>. BSA (0.05 g) was dissolved in a phosphate buffer (100 mL). BSA solution (0.1 mL) was pipetted into a micro-well plate followed by Na<sub>2</sub>SO<sub>4</sub> (0.3 M, 0.1 mL) and silver colloids (0.1 mL). The spectra were exposed for 1-10 s at a wavelength of 570 nm, 600 g/mm, 50 μm slits, and dynamic auto background subtraction. The pH of the BSA solution was adjusted with Na<sub>2</sub>SO<sub>4</sub> and H<sub>2</sub>SO<sub>4</sub> until the desired pH (2, 4, 6, and 10) was reached.

### Nanoparticle Films

Silver nanoparticle film preparation was adapted from Natan<sup>7</sup>. Small glass pieces were soaked in piranha (4 parts 35 % H<sub>2</sub>O<sub>2</sub>; 1 part conc. H<sub>2</sub>SO<sub>4</sub>) for 10 minutes, rinsed in methanol, and soaked in an alkoxy silane solution (4 part methanol: 1 part 3-aminopropyl trimethoxysilane) for 48 hours. Slides were rinsed with deionized water and soaked in colloid solution for 24 hours.

## Instrumentation

Home built Raman Microscope was used to obtain SERS spectra:

- Laser- Spectra Physics, Excelsior, 532 nm, 150 mW
- Microscope- Leica DMLM, 20x objective
- Beam Splitter- Omega Optical 540 DRLP
- Edge Filter- Razor Edge LWP filter, 532 nm, U-Grade, 25 mm
- Monochromator- CVI Digikrom 240, 600 gr/mm grating, 50 μm slit width

Detector- Apogee thermoelectrically cooled CCD




Figure 1. A picture of the Raman spectrometer.

## Results




Figure 2. Raman spectrum of pure BSA with 10 second exposure.

Table 1. Tentative peak assignments from Figure 2.

Raman Shift (cm <sup>-1</sup> )	Assignments
752	tryptophan (Trp)
854	tyrosine (Tyr)
1006	phenylalanine (Phe)
1334	alpha helix- amide 3
1448	CH <sub>2</sub>
1606	tyrosine or phenylalanine
1654	alpha helix- amide 1




Figure 3. SERS spectra of BSA solution with varying pHs (In descending order, 10, 6, 4, and 2).




Figure 4. SERS spectrum of BSA (pH 4) with 2 second exposure in colloid solution.

Table 2. Tentative Raman shift assignments for the bands shown in Figure 4.

Raman Shift (cm <sup>-1</sup> )	Assignments
833	tyrosine (Tyr)
1040	tryptophan(Trp)
1165	phenylalanine (Phe)
1297	alpha-helix amide 3
1367	tryptophan (Trp)
1574	tyrosine (Tyr)




Figure 5. SERS spectrum of BSA on silver nanoparticle film.

Table 3. Tentative Raman shift assignments for the bands shown in Figure 5

Raman Shift (cm <sup>-1</sup> )	Assignments
829	tyrosine (Tyr)
1038	tryptophan (Trp)
1158	phenylalanine (Phe)
1290	alpha-helix amide 3
1339	tryptophan (Trp)
1566	tyrosine (Tyr)

## Conclusions

Surface enhanced Raman scattering could be used to investigate label free detection of proteins by determining the secondary structure of the protein. The pH dependent spectra of BSA showed that when the pH of the protein was below its isoelectric point (pI), the more prominent the Raman bands. This was likely caused by the protein's increase in negative charge having a stronger attraction with the positively charged colloids. The optimal conditions of SERS for BSA were 500ug/mL and pH=4, however the optimal conditions for another protein could be very different because proteins interact differently with the colloids and have different pIs.

The observed vibrations in SERS identifies which part of the molecule is interacting with the silver colloids. The various amino acid stretches help depict the overall conformation of molecule. The amide stretches determine the secondary structure of the molecule. In the spectra of BSA, the amide stretches show a alpha-helical structure. The similar spectra between the colloidal solution and the nanoparticle film shows that BSA is orienting itself in the same manor such that the same amino acid residues are interacting with the colloids.

SERS is an important process to explore because label free detection of molecules can form a hypothesis about the functions and interactions of the compound in its environment. Further investigation with this process could lead to the discovery of new proteins and a better understanding of protein interactions in their existing environments.

## Literature cited

- 1.Xiao, H.; Hui, J.; Yan ,W.; Zhi, L.; Chun, W.; Wei, X.; Bing, Z.; Yukihiko, O. *Analytical Chemistry* **2008**, *8*, 2799-2804.
- 2.Kumar, P.; Reddy, A.; Arif, M.; Kundu, T.; Narayana, C. *The Journal of Physical Chemistry B*. **2006**, *33*, 16787-16792.
- 3.Carter, D.C.; Ho, J.X. *Adv Protein Chem Struct Serum Albumin*. **1994**, *45*, 153-203.
- 4.Cavalu, S.; Cinta-Pinzaru, S.; Leopold, N.; Keifer, W. *Biopolymers (Biospectroscopy)* .**62**, 341-348.; John Wiley & Sons: New York, 2001.
- 5.Ahern, A.; Garrell, R. *Langmuir*. **1991**, *2*, 254-261.
- 6.Lee, P.C.; Meisel, D. *The Journal of Physical Chemistry*. **1982**, *17*, 3391-3395
7. Keating C.d.,Kovaleski K.M., Natan M.J. *J Phys Chem B*. 1988, *102*, 9404-9413

## Acknowledgments

- Linfield student-faculty collaboration research grant
- Dr. Brian Gilbert
- Dr. Anne Kruchten
- Dylan Sorber
- Amanda Wolf
- Sean Boedeker
- Katie Corp

## For further information

Please contact [jreyes@linfield.edu](mailto:jreyes@linfield.edu) or [bgilber@linfield.edu](mailto:bgilber@linfield.edu). More information on this and related projects can be obtained at [www.linfield.edu](http://www.linfield.edu)